



**Bo'ness Road, Grangemouth
Stirlingshire, FK3 9XF
Tel: +44(0)1506 847710
E-mail: sales@dklmetals.co.uk
Internet: www.dklmetals.co.uk**

Technical Datasheet

Clearflow M1

Cored Solder Wire with Activated Rosin Flux

Applications

DKL Clearflow M1 is a new product developed for all lead-free solder alloys and applications. The new activator system is based on a previous successful activator. Clearflow M1 is designed for applications where higher activation with less residues are required.

Product Description

Clearflow M1 is a halide containing, rosin based no clean solder wire. The standard flux content is 2.2 % but 1.1%, 3.3% and 4.6% are also available. The activator of Clearflow M1 is designed to meet the higher temperature requirements for lead free alloys. Clearflow M1 shows good thermal stability due to a synthetic modified resin. The post soldering residues, can be left on the board without cleaning. Clearflow M1 is available in a variety of lead-free alloys e.g. SnCu0,7; SN100C, SN96C (SAC 387) and SN97C (SAC 305) and is supplied in a wide range of diameters from 0.2 – 3.25mm on 250g, 500g and 1kg reels.

Performance Characteristics:

- Classified per J-STD-004B as: ROM1
- Classified per EN 61190-1-1: ROM1
- Metal classified per EN 61190-1-3.
- RoHS and REACH compliant*
- Compatible with RoHS compliant solder masks
- Excellent solderability
- Clear hard residues

- Copper Mirror Corrosion: Pass
Tested to J-STD-004A/B, IPC-TM-650, Method 2.3.32
- Silver Chromate Test: Positive
Tested to J-STD-004B, IPC-TM-650, Method 2.3.33
- Chlorides and Bromides: 1.5%
Tested to J-STD-004B, IPC-TM-650, Method 2.3.35
- Corrosion Test: Pass
Tested to J-STD-004A/B, IPC-TM-650, Method 2.6.15
- Fluoride by Spot Test: Pass
Tested to J-STD-004B, IPC-TM-650, Method 2.3.35.1
- SIR, IPC:
Tested to J-STD-004, IPC-TM-650, Method 2.6.3.3
Test board 0,2mm spaces, 3mm lines, 5Volt bias voltage**
- Electrochemical migration: Pass
Test board 0,2mm spaces, 3mm lines; 5Volt bias voltage
Data given for SN100C, 1.1%, ø1mm

Patent Information:

DKL Metals Ltd offer licensed products:
SN100C-SnCu0,7Ni (EU 0985486; JPN 3152945; US 6180055)

SN96C-SnAg3,8Cu0,7 (JPN 3027441; US 5527628)

* Clearflow M1 contains no substances in concentrations which are prohibited by the European legislation 2002/95/EG ("RoHS").

Physical Properties:

- Acid Number: $200 \pm 5\%$ mg KOH/g of flux
Tested to J-STD-004, IPC-TM-650, Method 2.3.13
- Spread Test: $138 \text{ mm}^2 \pm 15\text{mm}^2$
Tested to DIN EN ISO 9455-10:2000 (alloy SN100C)

Application:

Clearflow M1 is suitable for hand and robotic soldering operations where fast wetting and defect free soldering is required. Due to the wide range of diameters available it is easy to select the correct size to suit the application being soldered.

Clearflow M1

Packaging:

Reel weight	0.25 kg	0.5 kg	1 kg
Reel marking			Hafner
Reel height	57 mm	57 mm	
Reel diameter	66 mm	66 mm	
Reel hole diameter	21 mm	21 mm	
Packing (reels/carton)	10/20	10/20	

Standard Diameters/Flux Content:

Wire diameter	0.2, 0.3, 0.5, 0.6, 0.7, 1.0, 1.2, 1.6, 2.0, 2.5, 3.0, 3.25 mm
Flux content (M/M)	1.1, 2.2, 3.3, 4.6 %

Other diameters and flux contents available on request.

Physical Properties Lead Free Alloys:

Clearflow M1 cored solder wire is available in the following lead-free alloys:

Alloy Name	Composition	Melting Point (°C)	Tensile Strength* 10mm/min (Mpa)	Strain* (%)
SN100C	SnCu0,7Ni	227	32	48
SN96C	SnAg3,8Cu0,7	217	52	27
SN97C	SnAg3,0Cu0,5	217-220	50	32
SnAg4	Sn96Ag4	221	46	33
SNSb5	Sn95Sb5	235-240	46	38
SnCu3	Sn97Cu3	227-310	55	22
SnCu0,7	Sn99,3Cu0,7	227	32	48
BiSn42	Bi58Sn42	138	75	33

Further alloys are available on request. *Mechanical properties from bulk samples.

Max. Impurity level of SN100C

Sn	Cu	Ni	Pb	Sb	Bi	Ag	Zn	Fe	Al	As	Cd
Bal	0.6 ±0.1	*	0.05 max	0.05 max	0.03 max	0.05 max	0.002 max	0.02 max	0.002 max	0.03 max	0.002 max

Max. Impurity level of SN96C

Sn	Cu	Ni	Pb	Sb	Bi	Ag	Zn	Fe	Al	As	Cd
Bal	0.7 ±0.1	0.005 max	0.05 max	0.05 max	0.01 max	3.8 ±0.2	0.001 max	0.008 max	0.001 max	0.01 max	0.001 max

Storage/Shelf Life:

Store in a clean dry environment at normal room temperatures. Has a minimum 5 years shelf life.

Health & Safety:

Read the material safety data sheet and warning label before use.

DKL Clearflow M1 Cored Solder Wire is manufactured in the UK.

The information given in this technical data sheet is to the best of our knowledge accurate. It is intended to be helpful but no warranty is expressed or implied regarding the accuracy of such data. It is the user's responsibility to determine the suitability of his own use of the product described herein; and since conditions of use are beyond our control, we disclaim all liability with respect to the use of any material supplied by us. Nothing contained herein shall be construed as permission or as recommendations to practice any patented invention without a license from the patent owner nor as recommendation to use any product or to practise any patented invention without a license from the patent owner nor as recommendation to use any product or to practise any process in violation of any law or any government regulations.